



Architectural Coatings

SUN PROOF Exterior Flat 100% Acrylic Latex Paint

GENERAL DESCRIPTION

SUN PROOF Exterior 100% Acrylic Latex is specifically formulated to meet the performance requirements of the residential and commercial markets. The new and improved formula provides excellent durability, great dirt resistance, low temperature application and excellent adhesion. SUN PROOF can be used on properly prepared and primed new and previously painted exterior siding, doors, trim and windows. Vinyl siding and similar plastic composites should not be painted with a color darker than the original color. Painting vinyl siding or plastic composites with a darker color may cause them to warp.

PRODUCT DATA

PRODUCT TYPE: 100% Acrylic Latex
SHEEN: Flat: 2-5 @60°; 2-5 @85°
VOLUME SOLIDS\*: 41% +/- 2%
WEIGHT SOLIDS\*: 59% +/- 2%
WEIGHT/GALLON\*: 12.0 lbs. (5.4 kg) +/- 0.2 lbs. (91 g)
VOC\*: <50 g/L (0.4 lbs./gal.)

\*Product data calculated on product 72-110XI.

COVERAGE: Approximately 300-400 sq. ft. (27.9-37.2 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

RECOMMENDED SUBSTRATES

Table with 3 columns: Aluminum Siding, Brick, Concrete; Ferrous Metal, Fiber Cement, Masonry; Stucco, Vinyl Siding, Wood

Table with 2 columns: Wet Film Thickness: 4.0-5.3 mils; Wet Microns: 102-135; Dry Film Thickness: 1.6-2.2 mils; Dry Microns: 41-56

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

CONFORMANCE STANDARDS

VOC compliant in all regulated areas
MPI approved in category 10

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.
To Touch: 1 hour
To Recoat: 4 hours
To Full Cure: 30 days

TINTING AND BASE INFORMATION

Table with 2 columns: 72-45XI Super White; 72-110XI White/Pastel Base; 72-150XI Midtone Base\*; 72-300XI Ultra Deep Base\*

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement. For example, product applied at 35°F (2°C) would require a minimum of 24 hours before recoat.

\*Must be tinted before use.

CLEANUP: Clean tools with warm, soapy water.

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

FLASH POINT: Over 200°F (93°C)

FEATURES / BENEFITS

Features

- Excellent dry & wet adhesion
Great dirt resistance
Flash rust resistance
100% acrylic latex formulation
Low VOC, <50 g/L
Thick, full-bodied application
Provides mildew resistant coating
Durable, tough finish
Application down to 35°F (2°C)
MPI #10 approval

Benefits

- Minimizes cracking and peeling
Stays clean
Beauty lasts
Excellent longevity and overall durability
Meets the most stringent VOC regulations nationwide
Smooth application, minimizes drips and runs
Resists the formation of mold and mildew on the paint film
Resists chipping
Extends the painting season
Meets strict performance and aesthetic requirements

Read Label and Safety Data Sheet Prior to Use. See other cautions on last page.

## GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose and peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Repair all moisture problems. Blistering and peeling issues are commonly caused by moisture behind the paint film. Putty all nail holes, and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. When applied to an uncoated substrate, two coats are required, with the first coat acting as the primer. The appropriate specialty primer is recommended for special substrates such as tannin staining wood, hardboard, new or chalky masonry, and bare metal.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**ALUMINUM SIDING:** Aluminum siding may present potential adhesion problems. Prime prior to topcoating. A specialty primer may be required if the original painted surface has degraded to the substrate. Topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion.

**BRICK, CONCRETE, MASONRY and STUCCO:** New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended. Painting glazed brick is not recommended due to potential adhesion problems.

**FERROUS METAL:** The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

**FIBER CEMENT:** Fiber cement board may present potential adhesion, alkali burn, and efflorescence problems. New board should be aged for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 and the moisture content must be less than 12% prior to priming and topcoating. All cracks and opens seams should be caulked to prevent water penetration. Pre-primed board from the manufacturer may not be uniformly or completely sealed. It is recommended that an alkali resistant primer be applied to ensure complete and uniform sealing prior to topcoating.

**VINYL SIDING:** Vinyl siding may present potential adhesion problems. Topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion. Color selection for vinyl siding is limited. Do not paint vinyl siding with a color darker than the original to prevent potential warping due to heat absorption.

**WOOD:** Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

## LIMITATIONS OF USE

FOR EXTERIOR USE ONLY. Apply when air and surface temperatures are 35°F (2°C) and surface temperature is at least 5°F (3°C) above the dew point. For optimum application properties, bring material to at least 50°F (10°C) prior to application. Air and surface temperature must remain above 35°F (2°C) for the next 24 hours. Avoid painting late in the day when dew and condensation are likely to form or if rain or snow is expected. Do not apply in direct sunlight. Not recommended for use on steps or floors. PROTECT FROM FREEZING.

Vinyl siding and similar plastic composites should not be painted with a color darker than the original color. Painting vinyl siding or plastic composites with a darker color may cause them to warp. Color selection for use over vinyl siding is limited. For information, call 1-800-441-9695.

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae.

## RECOMMENDED PRIMERS

Aluminum Siding	17-921, 17-941NF
Brick	4-503, 4-603, 4-808, 4-809, 17-921
Concrete	4-503, 4-603, 4-808, 4-809, 17-921
Ferrous Metal	90-712, 90-912
Fiber Cement	4-503, 4-603, 17-921
Masonry	4-503, 4-603, 4-808, 4-809, 17-921
Stucco	4-503, 4-603, 4-808, 4-809, 17-921
Wood	17-921, 17-941NF
Vinyl Siding	17-921

## PACKAGING

Quart (946 mL)
1-Gallon (3.78 L)
5-Gallon (18.9 L)
Not all products are available in all sizes.

## APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

**Airless Spray:** Pressure 2000 psi, tip 0.015" - 0.021"

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brush:** Polyester/Nylon Brush

**Roller:** 3/8" - 3/4" nap roller cover

**Thinning:** No thinning is usually required.

### Permissible temperatures during application:

Material:	35 to 90°F	2 to 32°C
Ambient:	35 to 100°F	2 to 38°C
Substrate:	35 to 100°F	2 to 38°C

## PRECAUTIONS

### WARNING! HARMFUL IF SWALLOWED. CAUSES RESPIRATORY TRACT IRRITATION. MAY CAUSE ALLERGIC SKIN REACTION.

Sanding and grinding dusts may be harmful if inhaled. Do not swallow. Do not get on skin or clothing. Avoid breathing vapor or mist. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information.** **FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. In case of contact, immediately flush skin with plenty of water while removing contaminated clothing and shoes. Get medical attention if irritation develops. If inhaled, remove to fresh air. If experiencing respiratory symptoms call a POISON CENTER or doctor/physician. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2017 PPG Industries, Inc. All Rights Reserved. The PPG logo is a registered trademark and the PPG Paints Logo & Design is a trademark of PPG Industries Ohio, Inc. Sun Proof is a registered trademark of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.  
Architectural Coatings  
One PPG Place  
Pittsburgh, PA 15272  
www.ppgpaints.com

Technical Services  
1-800-441-9695  
1-888-807-5123 fax

Architect/Specifier  
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.  
2505, rue de la Metropole  
Longueuil (Quebec) Canada J4G 1E5

72-45XI - 6/2017

Made in the  
**USA**